



ENVIRONMENTAL PRODUCT DECLARATION

in accordance with ISO 14025 and EN 15804:2012 + A2:2019

Anodised sheet for architectural cladding



Owner of the declaration:Publisher and Programme holder:EUROPEAN ALUMINIUMDeclaration number:EPD-2023-0024Issue date:2023-11-20Valid until2028-11-19

www.european-aluminium.eu



GENERAL INFORMATION



| Owner of the declaration | Novelis Deutschland GmbH Hannoversche Str. 1 D-37075 Göttingen, Germany |
|--|--|
| | www.novelis.com |
| Manufacturer | Novelis Deutschland GmbH |
| | Hannoversche Str. 1 D-37075 Göttingen, Germany |
| Publisher and Programme holder | EUROPEAN ALUMINIUM AISBL |
| EUROPEAN ALUMINIUM Avenue des Nerviens 85 1040 Etterbeek – Belgium VAT: BE 0480.720.716 | Avenue des Nerviens 85 1040 Brussels, Belgium |
| info@european-aluminium.eu www.european-aluminium.eu | Paul Voss, Director General |
| The declaration is based on the Product Category | European Aluminium General Programme |
| Rules | Instructions version 3, 23 rd of September 2020 |
| Declared Unit | 1 m ² of Anodised sheet for architectural cladding |
| Scope of the Environmental Product Declaration | This EPD covers 1 m ² of Anodised sheet for architectural cladding type B73A J73A J73A-Up EQA. These EPD results have been calculated from an LCA tool for EPD, based on the LCA for expert database, initially realised by Thinkstep in 2013 and updated by Ecoinnovazione in 2019. Among the product family, one representative product has been selected and corresponding EPD results have been calculated based on specific bill of materials. The results generated by the collective tool can be considered as a good proxy to model Anodised sheet for architectural cladding produced by Novelis. The EPD may be used in a B2B context within the European Market. |
| Liability | The owner of the declaration is liable for the underlying manufacturing information and European Aluminium is not liable in this respect. |
| Disclaimers | This EPD cannot be used as a guarantee of the recycled content of the actual product sold on the market. A specific declaration may be asked from the supplier. |
| | The use of this EPD within BIM tools is in principle limited to the products explicitly included in the EPD. The scaling of results to model similar products can only be done if justified and transparently reported in the project report. Any responsibility regarding the misuse of this EPD by third parties is not accepted by the Programme Operator. |
| 'erification | Verifier |

| /erification | Verifier |
|---|-----------|
| EN15804:2012 +A2:2019 serves as core PCR | |
| completed by European Aluminium PCR 03/2020 | |
| Verification of the EPD by an independent third party | 111 |
| in accordance with ISO 14025 | that Went |
| Internally X Externally | |





1 PRODUCT

1.1 Product description and applications

This Environmental Product Declaration (EPD) is for business-to-business communication.

The product object of the EPD is Novelis coil anodised materials:

- B73A
- J73A
- J73A-Up
- EQA

The representative products are anodised sheets for industrial cladding of 1, 2 and 3 mm of Aluminium sheet thickness and 10, 15 and 20 μ m of anodic layer thickness. EPD results have been calculated for 9 representative products, which are detailed in Table 1.

Table 1 Details representative products

| ID | Name | Model | Aluminum sheet thickness (mm) | Anodic layer thickness (μm) |
|----|--|---|----------------------------------|--------------------------------|
| 1 | • B73A • J73A • J73A-Up • EQA | Anodised sheet for architectural cladding | 1 | 10 |
| 2 | • B73A • J73A • J73A-Up • EQA | Anodised sheet for architectural cladding | 1 | 15 |
| 3 | • B73A • J73A • J73A-Up • EQA | Anodised sheet for architectural cladding | 1 | 20 |
| 4 | B73A J73A J73A-Up EQA | Anodised sheet for architectural cladding | 2 | 10 |
| 5 | B73A J73A J73A-Up EQA | Anodised sheet for architectural cladding | 2 | 15 |
| 6 | B73A J73A J73A-Up EQA | Anodised sheet for architectural cladding | 2 | 20 |
| 7 | • B73A • J73A • J73A-Up • EQA | Anodised sheet for architectural cladding | 3 | 10 |
| 8 | B73A J73A J73A-Up EQA | Anodised sheet for architectural cladding | 3 | 15 |



Novelis

| 9 | Anodised sheet for architectural cladding | 3 | 20 |
|---|---|---|----|
|---|---|---|----|

1.2 Technical Data

B73A | J73A | J73A-Up | EQA anodised solid aluminium further combines excellent flatness with good deformation properties; is corrosion- UV- and scratch resistant; non-combustible and 100% recyclable.

According to the client requirements, anodised coils and sheets are produced from other anodising qualities made of alloy series EN-AW 1xxx (e.g. 1050A), 3xxx, 5xxx (e.g. 5005, 5754) or 6xxx (e.g. 6061) for which the precise composition and microstructure are optimized to satisfy the anodising requirements. On average, these anodised coils and sheets contain at least 95% of aluminium. The technical data related to these anodised aluminium coils and sheets are publicly available or can be provided by Novelis.

For the most up-to-date values of the technical data, please refer to the product specifications available on the Novelis website (<u>www.novelis.com</u>).

Most relevant standards for applications of aluminium sheet products in buildings are EN 485-2, EN 507, EN 508-2, EN 573-3, EN 1396, EN 13501-1, EN 14782, EN 14783, EN 13964/+A1. Please refer to the latest version of those standards.





1.3 Process description

The anodised sheet is produced using an aluminium sheet that undergoes a further anodization process which increases the resistance to atmospheric corrosion. Other auxiliary materials are used, as for example some acids (sulphuric acid) or alkalis (sodium hydroxide). The aluminium production and the rolling are described in European Aluminium's environmental profile report.

The production phase includes mainly the following steps:

- 1. Aluminium production and rolling
- 2. Continuous coil anodising

The main background production processes are reported in Figure 1.




Figure 1 Main production processes and components of the anodised sheet





The upstream aluminium processes have been modelled using European Aluminium LCI datasets for the primary aluminium production, recycling and remelting as described in the European Aluminium Environmental profile report 2018.

At the end-of-life stage, the coil coated aluminium sheets should be specifically dismantled and collected in order to be treated since the aluminium can be efficiently recycled. After having been collected, the coil coated aluminium sheets are treated through shredding and sorting.

1.4 Health and safety aspects during production and installation

Continuous anodising requires the use of acid and alkaline solutions as well as some organometallic salt for colouring purposes. All those processes are very well controlled and workers are not in direct contacts with those solutions or related emissions. Waste solutions are systematically collected and treated. There are no relevant aspects of occupational health and safety during the further processing and installation of the aluminium coil and sheet. Under normal installation, no measurable environmental impacts can be associated to use of anodised aluminium coil. There is no release of any substance from the REACH SVHC list during further processing or during the use phase.

1.5 Reference service life

Since the use phase is not modelled, no specific information can be given about the Reference Service Life. In normal use, aluminium building products are not altered or corroded over time. A regular cleaning (e.g. once a year) of the product suffices to secure a long service life. However, the use of highly alkaline (pH >10) or highly acidic (pH < 4) cleaning solutions should be avoided. In practice, a service life of 50 years can be assumed in normal use for such application.





2 LCA – CALCULATION RULES

2.1 Declared unit & bill of materials

The Bill of Materials of the analysed product is reported in Table 2. The declared unit corresponds to 1 m^2 of coil anodised aluminium sheet.

Table 2 Bill of materials (kg) of the declared unit for the product

| Sheet thickness (mm) | Aluminium mass (kg) |
|----------------------|---------------------|
| 1 | 2.70 |
| 2 | 5.40 |
| 3 | 8.10 |

2.2 System boundary

This EPD is from cradle to gate with modules C1-C4 and module D, as reported in Table 3.

The production stage (modules A1-A3) includes processes that provide materials and energy input for the system, manufacturing, and transport processes up to the factory gate, as well as waste processing. For the end-of-life, the default scenario defined in the General Product Instructions and detailed in 3.2 is applied.

| Pr | oducti | on | | allati on | | Use stage End-of-Life | | | | | Next product system | | | | | |
|--------------|-----------|---------------|--------------|--------------|-----|-----------------------|--------|-------------|---------------|--------------------|---------------------------|----------------|-----------|------------------|----------|---|
| Raw material | Transport | Manufacturing | Transport to | Installation | Use | Maintenance | Repair | Replacement | Refurbishment | Operational energy | Operational water | Deconstruction | Transport | Waste processing | Disposal | Reuse, recovery, recycling potential |
| 41 | A2 | A3 | A4 | A5 | B1 | B2 | В3 | B4 | B5 | B6 | B7 | C1 | C2 | С3 | C4 | D |
| х | х | х | х | ND | ND | ND | ND | ND | ND | ND | ND | Х | х | х | х | Х |

Table 3 Modules declared

Note: ND: Not Declared; X: Module included in the LCA.

Module A4 is declared for a distance of 1 km to give the possibility to adjust the resulting Environmental impacts depending on the specific distance at hand.

2.3 Energy mix

The model uses the European electricity mix (EU-28 Electricity grid mix (2019)). For details about the electricity modelling in the datasets: production of primary aluminium, extrusion, rolling and recycling please refer to the Environmental Profile Report 2018.

2.4 Allocation

The scrap which are produced along the production chain are recycled into the same production chain and are modelled as "closed-loop" within Module A. This recycling loop has been modelled in the LCA for expert model so that the Anodised sheet for architectural cladding is the only product exiting the gate. Hence, the production process does not deliver any co-products.





At the end-of-life stage, the anodised sheet for architectural cladding is sent to an end-of-life treatment which is modelled according to the scenario reported in 3.2. The environmental burdens and benefits of recycling and energy recovery are calculated in module D accordingly.

2.5 Assumptions and Cut-off criteria

The aluminium sheets are composed of a mix of 60% primary aluminium and 40% recycled aluminium. Such mix represents the typical sourcing of aluminium in Europe, all markets included. For the primary aluminium, a primary aluminium ingot consumption mix was considered (European production + net fraction of imports into Europe). Alloying elements were not considered, and a pure aluminium sheet has been assumed as a proxy.

2.6 Data quality

Representativeness

Technological: All primary and secondary data were modelled to be specific to the technologies or technology mixes under study. Where technology-specific data were unavailable, proxy data were used. For the aluminium production, extrusion profiles and recycling, the datasets described in the Environmental Profile Report 2018 of European Aluminium have been used and integrated with the EPD profile of the low carbon primary aluminium. The modelling reflects the specific BoM of the analysed products. Technological representativeness is considered as being very good.

Geographical: All primary data were collected specifically to the countries under study. Regarding secondary data, where EU region-specific data were unavailable, DE datasets were used. For the aluminium production, extrusion profiles and recycling, the datasets described in the Environmental Profile Report 2018 of European Aluminium have been used. Geographical representativeness is considered as being good.

Temporal: Primary data refer to the year 2021, and all secondary data come from the LCA for expert version 2021.2, including those on aluminium production, which are the most recent ones as described in the Environmental Profile Report 2018 of European Aluminium.

Completeness

All known operating data was taken into consideration in the analysis. Based on earlier studies conducted by European Aluminium, it can be assumed that the ignored processes or flows contribute to much less than 5% of the impact categories under review.

The process chain is considered sufficiently complete regarding the goal and scope of this study.

Overall, the data quality can be described as good.

2.7 Software and databases

These EPD results have been calculated from an LCA tool for EPD, based on the LCA for expert database. Currently, the EPD software is using the software LCA for expert version 2021.2.

2.8 Comparability

As a general rule, a comparison or evaluation of EPD data may be possible when all of the data to be compared has been drawn up in accordance with EN 15804 and the building context or product-specific characteristics are taken into consideration.



3 LCA – SCENARIOS AND ADDITIONAL INFORMATION

3.1 Scenario for additional modules

Module A4 is taken into consideration in this Declaration, and it has been modelled according to the information reported in Table 4.

Table 4 Module A4 – Transport to the building site

| Scenario information | Unit (expressed per DU) |
|---|--|
| Fuel type and consumption of vehicle or vehicle | Truck-trailer, Euro 4, 34 - 40t gross weight / 27t |
| type used for transport e.g. long-distance truck, | payload capacity, diesel driven |
| boat, etc. | |
| Distance | 1 km |
| Capacity utilisation (including empty returns) | 61 % |
| Bulk density of transported products | - |
| Volume capacity utilisation factor (factor = 1 or | Not applicable |
| <1 or ≥1 for compressed or nested packaged | |
| products) | |

3.2 Scenario for Mod. C1-C4

The default scenario for the end-of-life of the Anodised sheet for architectural cladding, as reported in the General Programme Instructions, is the following:

- collection rate: 99%;
- shredding efficiency: 99%;
- scrap recycled through refining process: 96,5%
- overall aluminium recycling rate: 95%

Table 5 reports the main parameters of the end-of-life scenarios for the main materials and components.





Table 5 Parameters of the end-of-life scenarios for the main materials and components, related to the DU

| Processes | Unit (expressed per FU or DU of components, products, or materials and by type of material) | B73A J73A J73A-Up EQA – 1 mm of aluminium sheets thickness and 10, 15, 20 μm of anodic layer thickness |
|--------------------|---|--|
| Collection process | Kg collected separately | Aluminium sheet: 2.67 kg |
| Recovery system | Kg for recycling | Aluminium sheet: 2.65 kg |
| Disposal | Kg to landfill | Aluminium sheet: 0.03 kg |

Table 6 Parameters of the end-of-life scenarios for the main materials and components, related to the DU

| Processes | Unit (expressed per FU or DU of components, products, or materials and by type of material) | B73A J73A J73A-Up EQA – 2 mm of aluminium sheets thickness and 10, 15, 20 μm of anodic layer thickness |
|--------------------|---|--|
| Collection process | Kg collected separately | Aluminium sheet: 5.35 kg |
| Recovery system | Kg for recycling | Aluminium sheet: 5.29 kg |
| Disposal | Kg to landfill | Aluminium sheet: 0.05 kg |

Table 7 Parameters of the end-of-life scenarios for the main materials and components, related to the DU

| Processes | Unit (expressed per FU or DU of components, products, or materials and by type of material) | B73A J73A J73A-Up EQA – 3 mm of aluminium sheets thickness and 10, 15, 20 μm of anodic layer thickness |
|--------------------|---|--|
| Collection process | Kg collected separately | Aluminium sheet: 8.02 kg |
| Recovery system | Kg for recycling | Aluminium sheet: 7.94 kg |
| Disposal | Kg to landfill | Aluminium sheet: 0.08 kg |

Note to Tables 5, 6 e 7:

Material collected separately: This amount refers to the waste stream collected separately per material before being subjected to shredding

Material for recycling: This amount refers to the waste stream sent to recycling per material after the shredding and/or sorting process.

Material for final deposition – aluminium: this amount includes the aluminium not collected separately and the shredding losses.





3.3 Scenario Mod. D

Module D includes:

- a transport from the scrap dealers to the recycling plants, considering an average distance of 200 km;
- recycling of Aluminium through refining;
- a net credit for the avoided production of primary aluminium;

The calculation of module D has been implemented in line with the General Programme Instructions of European Aluminium, thus based on the difference between the scrap used at the input and output side. In some cases, this may result in environmental burdens instead of environmental benefits if the product system is a net consumer of valuable secondary material.

3.4 Additional environmental information

In case of fire, aluminium is a non-combustible construction material (European Fire Class A1) in accordance with Commission Decision 96/603/EC (later amended by European Commission Decision 2000/605/EC to follow the new classification system defined in Commission Decision 2000/147/EC, where Class A1 substituted the former Class A), and does therefore not make any contribution to fire.



4 LCA RESULTS – ANODISED SHEET FOR ARCHITECTURAL CLADDING – 1 mm sheet thickness; 10, 15, 20 μm anodic layer

4.1 Core Environmental impacts indicators

Table 8 Core Environmental impacts indicators for 1 m^2 Anodised sheet for architectural cladding – 1 mm of aluminium sheet thickness and 10 μ m of anodic layer thickness

| Impact category | Unit | A1-A3 | A4 | C1 | C2 | С3 | C4 | D |
|---------------------|--------------------------------------|----------|-----------|----------|-----------|----------|-----------|-----------|
| GWP - total | kg CO ₂ eq. | 1.95E+01 | 1.67E-04 | 3.61E-01 | 3.32E-02 | 8.58E-02 | 7.91E-04 | -1.28E+01 |
| GWP – fossil | kg CO₂ eq. | 1.94E+01 | 1.66E-04 | 3.57E-01 | 3.31E-02 | 8.50E-02 | 8.12E-04 | -1.28E+01 |
| GWP – biogenic | kg CO₂ eq. | 5.21E-02 | -6.16E-07 | 3.81E-03 | -1.23E-04 | 5.28E-04 | -2.36E-05 | -2.67E-02 |
| GWP - luluc | kg CO₂ eq. | 4.89E-03 | 1.00E-06 | 6.40E-05 | 1.99E-04 | 2.07E-04 | 2.39E-06 | -2.17E-03 |
| ODP | kg CFC 11 eq. | 1.52E-10 | 2.93E-17 | 6.43E-12 | 5.82E-15 | 2.67E-15 | 3.16E-18 | -9.60E-11 |
| АР | mol H⁺ eq. | 9.22E-02 | 1.15E-06 | 7.66E-04 | 2.29E-04 | 1.46E-04 | 5.79E-06 | -7.43E-02 |
| EP - freshwater | kg PO ₄ ³⁻ eq. | 3.76E-05 | 3.90E-10 | 1.31E-06 | 7.75E-08 | 3.60E-07 | 1.36E-09 | -5.67E-06 |
| EP - marine | kg N eq. | 1.53E-02 | 5.76E-07 | 1.88E-04 | 1.15E-04 | 4.09E-05 | 1.50E-06 | -1.07E-02 |
| EP - terrestrial | mol N eq. | 1.65E-01 | 6.36E-06 | 1.97E-03 | 1.27E-03 | 4.27E-04 | 1.65E-05 | -1.16E-01 |
| РОСР | kg NMVOC eq. | 4.52E-02 | 1.09E-06 | 5.04E-04 | 2.17E-04 | 1.03E-04 | 4.55E-06 | -3.22E-02 |
| ADP-MM (**) | kg Sb eq. | 1.19E-05 | 1.18E-11 | 5.43E-08 | 2.36E-09 | 3.23E-08 | 7.67E-11 | -2.87E-06 |
| ADPF (**) | MJ | 2.68E+02 | 2.27E-03 | 7.39E+00 | 4.51E-01 | 1.08E+00 | 1.08E-02 | -1.57E+02 |
| WDP (**) | m ³ | 4.28E+00 | 8.70E-07 | 7.77E-02 | 1.73E-04 | 1.91E-03 | 8.72E-05 | -1.90E+00 |

Note: GWP – Global Warming Potential; ODP – Ozone Depletion; AP – acidification potential for soil and water; EP – Eutrophication potential; POCP – formation potential of tropospheric ozone; ADP - MM – abiotic depletion potential for non fossil resources; ADPF – Abiotic depletion potential for fossil resources; WDP – Water deprivation potential.



Table 9 Core Environmental impacts indicators for 1 m^2 Anodised sheet for architectural cladding - 1 mm of aluminium sheet thickness and 15 μ m of anodic layer thickness

| Impact category | Unit | A1-A3 | A4 | C1 | C2 | C3 | C4 | D |
|---------------------|------------------------|----------|-----------|----------|-----------|----------|-----------|-----------|
| GWP - total | kg CO₂ eq. | 1.96E+01 | 1.67E-04 | 3.61E-01 | 3.32E-02 | 8.58E-02 | 7.91E-04 | -1.28E+01 |
| GWP – fossil | kg CO₂ eq. | 1.96E+01 | 1.66E-04 | 3.57E-01 | 3.31E-02 | 8.50E-02 | 8.12E-04 | -1.28E+01 |
| GWP – biogenic | kg CO ₂ eq. | 5.27E-02 | -6.16E-07 | 3.81E-03 | -1.23E-04 | 5.28E-04 | -2.36E-05 | -2.67E-02 |
| GWP - luluc | kg CO₂ eq. | 4.90E-03 | 1.00E-06 | 6.40E-05 | 1.99E-04 | 2.07E-04 | 2.39E-06 | -2.17E-03 |
| ODP | kg CFC 11 eq. | 1.53E-10 | 2.93E-17 | 6.43E-12 | 5.82E-15 | 2.67E-15 | 3.16E-18 | -9.60E-11 |
| АР | mol H⁺ eq. | 9.23E-02 | 1.15E-06 | 7.66E-04 | 2.29E-04 | 1.46E-04 | 5.79E-06 | -7.43E-02 |
| EP - freshwater | kg PO₄³- eq. | 3.78E-05 | 3.90E-10 | 1.31E-06 | 7.75E-08 | 3.60E-07 | 1.36E-09 | -5.67E-06 |
| EP - marine | kg N eq. | 1.53E-02 | 5.76E-07 | 1.88E-04 | 1.15E-04 | 4.09E-05 | 1.50E-06 | -1.07E-02 |
| EP - terrestrial | mol N eq. | 1.66E-01 | 6.36E-06 | 1.97E-03 | 1.27E-03 | 4.27E-04 | 1.65E-05 | -1.16E-01 |
| РОСР | kg NMVOC eq. | 4.54E-02 | 1.09E-06 | 5.04E-04 | 2.17E-04 | 1.03E-04 | 4.55E-06 | -3.22E-02 |
| ADP-MM (**) | kg Sb eq. | 1.19E-05 | 1.18E-11 | 5.43E-08 | 2.36E-09 | 3.23E-08 | 7.67E-11 | -2.87E-06 |
| ADPF (**) | MJ | 2.70E+02 | 2.27E-03 | 7.39E+00 | 4.51E-01 | 1.08E+00 | 1.08E-02 | -1.57E+02 |
| WDP (**) | m ³ | 4.29E+00 | 8.70E-07 | 7.77E-02 | 1.73E-04 | 1.91E-03 | 8.72E-05 | -1.90E+00 |

Note: GWP – Global Warming Potential; ODP – Ozone Depletion; AP – acidification potential for soil and water; EP – Eutrophication potential; POCP – formation potential of tropospheric ozone; ADP - MM – abiotic depletion potential for non fossil resources; ADPF – Abiotic depletion potential for fossil resources; WDP – Water deprivation potential.



Table 10 Core Environmental impacts indicators for 1 m^2 Anodised sheet for architectural cladding – 1 mm of aluminium sheet thickness and 20 μ m of anodic layer thickness

| Impact category | Unit | A1-A3 | A4 | C1 | C2 | С3 | C4 | D |
|---------------------|--------------------------------------|----------|-----------|----------|-----------|----------|-----------|-----------|
| GWP - total | kg CO₂ eq. | 1.99E+01 | 1.67E-04 | 3.61E-01 | 3.32E-02 | 8.58E-02 | 7.91E-04 | -1.28E+01 |
| GWP – fossil | kg CO₂ eq. | 1.99E+01 | 1.66E-04 | 3.57E-01 | 3.31E-02 | 8.50E-02 | 8.12E-04 | -1.28E+01 |
| GWP – biogenic | kg CO₂ eq. | 5.50E-02 | -6.16E-07 | 3.81E-03 | -1.23E-04 | 5.28E-04 | -2.36E-05 | -2.67E-02 |
| GWP - luluc | kg CO₂ eq. | 4.92E-03 | 1.00E-06 | 6.40E-05 | 1.99E-04 | 2.07E-04 | 2.39E-06 | -2.17E-03 |
| ODP | kg CFC 11 eq. | 1.57E-10 | 2.93E-17 | 6.43E-12 | 5.82E-15 | 2.67E-15 | 3.16E-18 | -9.60E-11 |
| АР | mol H⁺ eq. | 9.28E-02 | 1.15E-06 | 7.66E-04 | 2.29E-04 | 1.46E-04 | 5.79E-06 | -7.43E-02 |
| EP - freshwater | kg PO ₄ ³⁻ eq. | 3.85E-05 | 3.90E-10 | 1.31E-06 | 7.75E-08 | 3.60E-07 | 1.36E-09 | -5.67E-06 |
| EP - marine | kg N eq. | 1.54E-02 | 5.76E-07 | 1.88E-04 | 1.15E-04 | 4.09E-05 | 1.50E-06 | -1.07E-02 |
| EP - terrestrial | mol N eq. | 1.67E-01 | 6.36E-06 | 1.97E-03 | 1.27E-03 | 4.27E-04 | 1.65E-05 | -1.16E-01 |
| РОСР | kg NMVOC eq. | 4.57E-02 | 1.09E-06 | 5.04E-04 | 2.17E-04 | 1.03E-04 | 4.55E-06 | -3.22E-02 |
| ADP-MM (**) | kg Sb eq. | 1.19E-05 | 1.18E-11 | 5.43E-08 | 2.36E-09 | 3.23E-08 | 7.67E-11 | -2.87E-06 |
| ADPF (**) | MJ | 2.76E+02 | 2.27E-03 | 7.39E+00 | 4.51E-01 | 1.08E+00 | 1.08E-02 | -1.57E+02 |
| WDP (**) | m ³ | 4.33E+00 | 8.70E-07 | 7.77E-02 | 1.73E-04 | 1.91E-03 | 8.72E-05 | -1.90E+00 |

Note: GWP – Global Warming Potential; ODP – Ozone Depletion; AP – acidification potential for soil and water; EP – Eutrophication potential; POCP – formation potential of tropospheric ozone; ADP - MM – abiotic depletion potential for non fossil resources; ADPF – Abiotic depletion potential for fossil resources; WDP – Water deprivation potential.





4.1.1 Additional Environmental impacts indicators

Table 11 Additional Environmental impacts indicators for 1 m^2 Anodised sheet for architectural cladding – 1 mm of aluminium sheet thickness and 10 μ m of anodic layer thickness

| Impact category | Unit | A1-A3 | A4 | C1 | C2 | С3 | C4 | D |
|---|--------------------------|----------|----------|----------|----------|----------|----------|-----------|
| Particular Matter emissions | Disease inciden ce | 1.21E-06 | 3.82E-12 | 6.51E-09 | 7.61E-10 | 1.08E-09 | 7.19E-11 | -1.04E-06 |
| lonising radiation - human health (*) | [kBq U235 eq.] | 3.18E+00 | 2.44E-07 | 1.94E-01 | 4.87E-05 | 9.98E-03 | 1.19E-05 | -1.79E+00 |
| Eco-toxicity (freshwate r) (**) | [CTUe] | 8.54E+01 | 1.69E-03 | 3.28E+00 | 3.36E-01 | 4.29E-01 | 6.14E-03 | -5.17E+01 |
| Human toxicity - cancer effects (**) | [CTUh] | 4.46E-09 | 3.37E-14 | 1.09E-10 | 6.70E-12 | 5.93E-11 | 9.06E-13 | -3.22E-09 |
| Human toxicity - non-cancer effects (**) | [CTUh] | 1.34E-07 | 1.81E-12 | 2.70E-09 | 3.61E-10 | 4.89E-10 | 1.00E-10 | -9.28E-08 |
| Land Use related impacts/ Soil quality (**) | dimensi onless | 2.98E+01 | 8.05E-04 | 2.90E+00 | 1.60E-01 | 5.32E-01 | 2.18E-03 | -4.54E+00 |

(*) **Disclaimer**: This impact category deals mainly with the eventual impact of low dose ionizing radiation on human health of the nuclear fuel cycle. It does not consider effects due to possible nuclear accidents, occupational exposure nor due to radioactive waste disposal in underground facilities. Potential ionizing radiation from the soil, from radon and from some construction materials is also not measured by this indicator.



Table 12 Additional Environmental impacts indicators for $1 m^2$ Anodised sheet for architectural cladding - 1 mm of aluminium sheet thickness and $15 \mu m$ of anodic layer thickness

| Impact category | Unit | A1-A3 | A4 | C1 | C2 | C3 | C4 | D |
|---|--------------------------|----------|----------|----------|----------|----------|----------|-----------|
| Particular Matter emissions | Disease inciden ce | 1.21E-06 | 3.82E-12 | 6.51E-09 | 7.61E-10 | 1.08E-09 | 7.19E-11 | -1.04E-06 |
| lonising radiation - human health (*) | [kBq U235 eq.] | 3.20E+00 | 2.44E-07 | 1.94E-01 | 4.87E-05 | 9.98E-03 | 1.19E-05 | -1.79E+00 |
| Eco-toxicity (freshwate r) (**) | [CTUe] | 8.58E+01 | 1.69E-03 | 3.28E+00 | 3.36E-01 | 4.29E-01 | 6.14E-03 | -5.17E+01 |
| Human toxicity - cancer effects (**) | [CTUh] | 4.49E-09 | 3.37E-14 | 1.09E-10 | 6.70E-12 | 5.93E-11 | 9.06E-13 | -3.22E-09 |
| Human toxicity - non-cancer effects (**) | [CTUh] | 1.35E-07 | 1.81E-12 | 2.70E-09 | 3.61E-10 | 4.89E-10 | 1.00E-10 | -9.28E-08 |
| Land Use related impacts/ Soil quality (**) | dimensi onless | 3.02E+01 | 8.05E-04 | 2.90E+00 | 1.60E-01 | 5.32E-01 | 2.18E-03 | -4.54E+00 |

(*) **Disclaimer**: This impact category deals mainly with the eventual impact of low dose ionizing radiation on human health of the nuclear fuel cycle. It does not consider effects due to possible nuclear accidents, occupational exposure nor due to radioactive waste disposal in underground facilities. Potential ionizing radiation from the soil, from radon and from some construction materials is also not measured by this indicator.



Table 13 Additional Environmental impacts indicators for $1 m^2$ Anodised sheet for architectural cladding – 1 mm of aluminium sheet thickness and 20 μ m of anodic layer thickness

| Impact category | Unit | A1-A3 | A4 | C1 | C2 | C3 | C4 | D |
|---|--------------------------|----------|----------|----------|----------|----------|----------|-----------|
| Particular Matter emissions | Disease inciden ce | 1.21E-06 | 3.82E-12 | 6.51E-09 | 7.61E-10 | 1.08E-09 | 7.19E-11 | -1.04E-06 |
| lonising radiation - human health (*) | [kBq U235 eq.] | 3.31E+00 | 2.44E-07 | 1.94E-01 | 4.87E-05 | 9.98E-03 | 1.19E-05 | -1.79E+00 |
| Eco-toxicity (freshwate r) (**) | [CTUe] | 8.77E+01 | 1.69E-03 | 3.28E+00 | 3.36E-01 | 4.29E-01 | 6.14E-03 | -5.17E+01 |
| Human toxicity - cancer effects (**) | [CTUh] | 4.56E-09 | 3.37E-14 | 1.09E-10 | 6.70E-12 | 5.93E-11 | 9.06E-13 | -3.22E-09 |
| Human toxicity - non-cancer effects (**) | [CTUh] | 1.37E-07 | 1.81E-12 | 2.70E-09 | 3.61E-10 | 4.89E-10 | 1.00E-10 | -9.28E-08 |
| Land Use related impacts/ Soil quality (**) | dimensi onless | 3.18E+01 | 8.05E-04 | 2.90E+00 | 1.60E-01 | 5.32E-01 | 2.18E-03 | -4.54E+00 |

(*) **Disclaimer**: This impact category deals mainly with the eventual impact of low dose ionizing radiation on human health of the nuclear fuel cycle. It does not consider effects due to possible nuclear accidents, occupational exposure nor due to radioactive waste disposal in underground facilities. Potential ionizing radiation from the soil, from radon and from some construction materials is also not measured by this indicator.



4.2 Resource use

Table 14 Resource use for 1 m^2 Anodised sheet for architectural cladding - 1 mm of aluminium sheet thickness and 10 μ m of anodic layer thickness

| Parameter | Unit | A1-A3 | A4 | C1 | C2 | С3 | C4 | D |
|-----------|------|----------|----------|----------|----------|----------|----------|-----------|
| PERE | MJ | 1.05E+02 | 1.47E-04 | 4.39E+00 | 2.92E-02 | 5.81E-01 | 1.45E-03 | -7.12E+01 |
| PERM | MJ | 0.00E+00 |
| PERT | MJ | 1.05E+02 | 1.47E-04 | 4.39E+00 | 2.92E-02 | 5.81E-01 | 1.45E-03 | -7.12E+01 |
| PENRE | MJ | 2.68E+02 | 2.27E-03 | 7.39E+00 | 4.52E-01 | 1.08E+00 | 1.08E-02 | -1.57E+02 |
| PENRM | MJ | 0.00E+00 |
| PENRT | MJ | 2.68E+02 | 2.27E-03 | 7.39E+00 | 4.52E-01 | 1.08E+00 | 1.08E-02 | -1.57E+02 |
| SM | kg | 1.17E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 |
| RSF | MJ | 0.00E+00 |
| NRSF | MJ | 0.00E+00 |
| FW | m³ | 2.57E-01 | 1.34E-07 | 3.54E-03 | 2.66E-05 | 3.13E-04 | 2.66E-06 | -1.80E-01 |

Note: PERE – use of renewable primary energy resources used as raw materials; PERT – Total use of renewable primary energy resources; PENRE – use of non-renewable primary energy excluding non-renewable primary energy resources used as raw materials; PENRM – use of non-renewable primary energy resources used as raw materials; PENRT – Total use of non-renewable primary energy resources used as raw materials; PENRT – Total use of non-renewable primary energy resources used as raw materials; PENRT – Total use of non-renewable primary energy resources used as raw materials; PENRT – Total use of non-renewable primary energy resources used as raw materials; PENRT – Total use of non-renewable primary energy resources; SM – Use of secondary materials; RSF – Use of renewable secondary fuels; NRSF – use of non-renewable secondary fuels; FW – use of net fresh water.

Table 15 Resource use for 1 m^2 Anodised sheet for architectural cladding - 1 mm of aluminium sheet thickness and 15 μ m of anodic layer thickness

| Parameter | Unit | A1-A3 | A4 | C1 | C2 | C3 | C4 | D |
|-----------|------|----------|----------|----------|----------|----------|----------|-----------|
| PERE | MJ | 1.05E+02 | 1.47E-04 | 4.39E+00 | 2.92E-02 | 5.81E-01 | 1.45E-03 | -7.12E+01 |
| PERM | MJ | 0.00E+00 |
| PERT | MJ | 1.05E+02 | 1.47E-04 | 4.39E+00 | 2.92E-02 | 5.81E-01 | 1.45E-03 | -7.12E+01 |
| PENRE | MJ | 2.70E+02 | 2.27E-03 | 7.39E+00 | 4.52E-01 | 1.08E+00 | 1.08E-02 | -1.57E+02 |
| PENRM | MJ | 0.00E+00 |
| PENRT | MJ | 2.70E+02 | 2.27E-03 | 7.39E+00 | 4.52E-01 | 1.08E+00 | 1.08E-02 | -1.57E+02 |
| SM | kg | 1.17E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 |
| RSF | MJ | 0.00E+00 |
| NRSF | MJ | 0.00E+00 |
| FW | m³ | 2.58E-01 | 1.34E-07 | 3.54E-03 | 2.66E-05 | 3.13E-04 | 2.66E-06 | -1.80E-01 |

Note: PERE – use of renewable primary energy resources used as raw materials; PERT – Total use of renewable primary energy resources; PENRE – use of non-renewable primary energy excluding non-renewable primary energy resources used as raw materials; PENRM – use of non-renewable primary energy resources used as raw materials; PENRT – Total use of non-renewable primary energy resources used as raw materials; PENRT – Total use of non-renewable primary energy resources used as raw materials; PENRT – Total use of non-renewable primary energy resources used as raw materials; PENRT – Total use of non-renewable primary energy resources used as raw materials; PENRT – Total use of non-renewable primary energy resources; SM – Use of secondary materials; RSF – Use of renewable secondary fuels; NRSF – use of non-renewable secondary fuels; FW – use of net fresh water.



Table 16 Resource use for 1 m^2 Anodised sheet for architectural cladding - 1 mm of aluminium sheet thickness and 20 μ m of anodic layer thickness

| Parameter | Unit | A1-A3 | A4 | C1 | C2 | С3 | C4 | D |
|-----------|------|----------|----------|----------|----------|----------|----------|-----------|
| PERE | MJ | 1.08E+02 | 1.47E-04 | 4.39E+00 | 2.92E-02 | 5.81E-01 | 1.45E-03 | -7.12E+01 |
| PERM | MJ | 0.00E+00 |
| PERT | MJ | 1.08E+02 | 1.47E-04 | 4.39E+00 | 2.92E-02 | 5.81E-01 | 1.45E-03 | -7.12E+01 |
| PENRE | MJ | 2.76E+02 | 2.27E-03 | 7.39E+00 | 4.52E-01 | 1.08E+00 | 1.08E-02 | -1.57E+02 |
| PENRM | MJ | 0.00E+00 |
| PENRT | MJ | 2.76E+02 | 2.27E-03 | 7.39E+00 | 4.52E-01 | 1.08E+00 | 1.08E-02 | -1.57E+02 |
| SM | kg | 1.17E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 |
| RSF | MJ | 0.00E+00 |
| NRSF | MJ | 0.00E+00 |
| FW | m³ | 2.60E-01 | 1.34E-07 | 3.54E-03 | 2.66E-05 | 3.13E-04 | 2.66E-06 | -1.80E-01 |

Note: PERE – use of renewable primary energy resources used as raw materials; PERT – Total use of renewable primary energy resources; PENRE – use of non-renewable primary energy excluding non-renewable primary energy resources used as raw materials; PENRM – use of non-renewable primary energy resources used as raw materials; PENRT – Total use of non-renewable primary energy resources used as raw materials; PENRT – Total use of non-renewable primary energy resources used as raw materials; PENRT – Total use of non-renewable primary energy resources used as raw materials; PENRT – Total use of non-renewable primary energy resources; SM – Use of secondary materials; RSF – Use of renewable secondary fuels; NRSF – use of non-renewable secondary fuels; FW – use of net fresh water.



4.3 Output flows, waste categories

Table 17 Output flows, waste categories for 1 m^2 Anodised sheet for architectural cladding - 1 mm of aluminium sheet thickness and 10 μ m of anodic layer thickness

| Parameter | Unit | A1-A3 | A4 | C1 | C2 | С3 | C4 | D |
|-----------|------|----------|----------|-----------|----------|----------|----------|-----------|
| HWD | kg | 1.53E-07 | 6.08E-15 | -5.74E-10 | 1.21E-12 | 8.36E-10 | 1.14E-12 | -1.11E-07 |
| NHWD | kg | 4.48E+00 | 3.31E-07 | 5.38E-03 | 6.58E-05 | 1.11E-03 | 5.38E-02 | -3.83E+00 |
| RWD | kg | 1.78E-02 | 2.37E-09 | 1.17E-03 | 4.72E-07 | 1.01E-04 | 1.13E-07 | -9.36E-03 |
| CRU | kg | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 |
| MFR | kg | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 2.65E+00 | 0.00E+00 | 0.00E+00 |
| MER | kg | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 |
| EEE | MJ | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 |
| EET | MJ | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 |

Note: HWD – hazardous waste disposed; NHWD – Non-hazardous waste disposed; RWD – Radioactive waste disposed; CRU – Components for re-use; MFR – Materials for recycling; MER – Materials for energy recovery; EEE – Exported electrical energy; EET – Exported thermal energy

Table 18 Output flows, waste categories for 1 m^2 Anodised sheet for architectural cladding - 1 mm of aluminium sheet thickness and 15 μ m of anodic layer thickness

| Parameter | Unit | A1-A3 | A4 | C1 | C2 | С3 | C4 | D |
|-----------|------|----------|----------|-----------|----------|----------|----------|-----------|
| HWD | kg | 1.53E-07 | 6.08E-15 | -5.74E-10 | 1.21E-12 | 8.36E-10 | 1.14E-12 | -1.11E-07 |
| NHWD | kg | 4.48E+00 | 3.31E-07 | 5.38E-03 | 6.58E-05 | 1.11E-03 | 5.38E-02 | -3.83E+00 |
| RWD | kg | 1.80E-02 | 2.37E-09 | 1.17E-03 | 4.72E-07 | 1.01E-04 | 1.13E-07 | -9.36E-03 |
| CRU | kg | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 |
| MFR | kg | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 2.65E+00 | 0.00E+00 | 0.00E+00 |
| MER | kg | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 |
| EEE | MJ | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 |
| EET | MJ | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 |

Note: HWD – hazardous waste disposed; NHWD – Non-hazardous waste disposed; RWD – Radioactive waste disposed; CRU – Components for re-use; MFR – Materials for recycling; MER – Materials for energy recovery; EEE – Exported electrical energy; EET – Exported thermal energy

Table 19 Output flows, waste categories for 1 m^2 Anodised sheet for architectural cladding - 1 mm of aluminium sheet thickness and 20 μ m of anodic layer thickness

| Parameter | Unit | A1-A3 | A4 | C1 | C2 | С3 | C4 | D |
|-----------|------|----------|----------|-----------|----------|----------|----------|-----------|
| HWD | kg | 1.53E-07 | 6.08E-15 | -5.74E-10 | 1.21E-12 | 8.36E-10 | 1.14E-12 | -1.11E-07 |
| NHWD | kg | 4.49E+00 | 3.31E-07 | 5.38E-03 | 6.58E-05 | 1.11E-03 | 5.38E-02 | -3.83E+00 |
| RWD | kg | 1.86E-02 | 2.37E-09 | 1.17E-03 | 4.72E-07 | 1.01E-04 | 1.13E-07 | -9.36E-03 |
| CRU | kg | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 |
| MFR | kg | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 2.65E+00 | 0.00E+00 | 0.00E+00 |
| MER | kg | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 |
| EEE | MJ | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 |
| EET | MJ | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 |

Note: HWD – hazardous waste disposed; NHWD – Non-hazardous waste disposed; RWD – Radioactive waste disposed; CRU – Components for re-use; MFR – Materials for recycling; MER – Materials for energy recovery; EEE – Exported electrical energy; EET – Exported thermal energy



5 LCA RESULTS – ANODISED SHEET FOR ARCHITECTURAL CLADDING – 2 mm sheet thickness; 10, 15, 20 μm anodic layer

5.1 Core Environmental impacts indicators

Table 20 Core Environmental impacts indicators for 1 m^2 Anodised sheet for architectural cladding – 2 mm of aluminium sheet thickness and 10 μ m of anodic layer thickness

| Impact category | Unit | A1-A3 | A4 | C1 | C2 | С3 | C4 | D |
|---------------------|-----------------|----------|-----------|----------|-----------|----------|-----------|-----------|
| GWP - total | kg CO₂ eq. | 3.55E+01 | 3.33E-04 | 7.31E-01 | 6.63E-02 | 1.72E-01 | 1.58E-03 | -2.56E+01 |
| GWP – fossil | kg CO₂ eq. | 3.54E+01 | 3.32E-04 | 7.23E-01 | 6.62E-02 | 1.70E-01 | 1.62E-03 | -2.56E+01 |
| GWP – biogenic | kg CO₂ eq. | 5.79E-02 | -1.23E-06 | 7.59E-03 | -2.45E-04 | 1.06E-03 | -4.72E-05 | -5.34E-02 |
| GWP - luluc | kg CO₂ eq. | 9.44E-03 | 2.00E-06 | 1.80E-04 | 3.98E-04 | 4.14E-04 | 4.77E-06 | -4.34E-03 |
| ODP | kg CFC 11 eq. | 2.72E-10 | 5.85E-17 | 1.29E-11 | 1.16E-14 | 5.34E-15 | 6.31E-18 | -1.92E-10 |
| АР | mol H⁺ eq. | 1.78E-01 | 2.31E-06 | 1.58E-03 | 4.59E-04 | 2.92E-04 | 1.16E-05 | -1.49E-01 |
| EP - freshwater | kg PO₄³- eq. | 4.78E-05 | 7.79E-10 | 2.64E-06 | 1.55E-07 | 7.19E-07 | 2.73E-09 | -1.13E-05 |
| EP - marine | kg N eq. | 2.91E-02 | 1.15E-06 | 3.97E-04 | 2.29E-04 | 8.17E-05 | 3.00E-06 | -2.13E-02 |
| EP - terrestrial | mol N eq. | 3.16E-01 | 1.27E-05 | 4.18E-03 | 2.53E-03 | 8.54E-04 | 3.30E-05 | -2.33E-01 |
| РОСР | kg NMVOC eq. | 8.67E-02 | 2.18E-06 | 1.07E-03 | 4.35E-04 | 2.06E-04 | 9.10E-06 | -6.45E-02 |
| ADP-MM (**) | kg Sb eq. | 1.54E-05 | 2.37E-11 | 1.09E-07 | 4.71E-09 | 6.46E-08 | 1.53E-10 | -5.75E-06 |
| ADPF (**) | MJ | 4.73E+02 | 4.54E-03 | 1.49E+01 | 9.03E-01 | 2.15E+00 | 2.16E-02 | -3.13E+02 |
| WDP (**) | m ³ | 6.53E+00 | 1.74E-06 | 1.55E-01 | 3.46E-04 | 3.82E-03 | 1.74E-04 | -3.80E+00 |

Note: GWP – Global Warming Potential; ODP – Ozone Depletion; AP – acidification potential for soil and water; EP – Eutrophication potential; POCP – formation potential of tropospheric ozone; ADP - MM – abiotic depletion potential for non fossil resources; ADPF – Abiotic depletion potential for fossil resources; WDP – Water deprivation potential.



Table 21 Core Environmental impacts indicators for 1 m^2 Anodised sheet for architectural cladding - 2 mm of aluminium sheet thickness and 15 μ m of anodic layer thickness

| Impact category | Unit | A1-A3 | A4 | C1 | C2 | C3 | C4 | D |
|---------------------|--------------------------------------|----------|-----------|----------|-----------|----------|-----------|-----------|
| GWP - total | kg CO₂ eq. | 3.56E+01 | 3.33E-04 | 7.31E-01 | 6.63E-02 | 1.72E-01 | 1.58E-03 | -2.56E+01 |
| GWP – fossil | kg CO₂ eq. | 3.56E+01 | 3.32E-04 | 7.23E-01 | 6.62E-02 | 1.70E-01 | 1.62E-03 | -2.56E+01 |
| GWP – biogenic | kg CO₂ eq. | 5.86E-02 | -1.23E-06 | 7.59E-03 | -2.45E-04 | 1.06E-03 | -4.72E-05 | -5.34E-02 |
| GWP - luluc | kg CO₂ eq. | 9.44E-03 | 2.00E-06 | 1.80E-04 | 3.98E-04 | 4.14E-04 | 4.77E-06 | -4.34E-03 |
| ODP | kg CFC 11 eq. | 2.73E-10 | 5.85E-17 | 1.29E-11 | 1.16E-14 | 5.34E-15 | 6.31E-18 | -1.92E-10 |
| AP | mol H⁺ eq. | 1.78E-01 | 2.31E-06 | 1.58E-03 | 4.59E-04 | 2.92E-04 | 1.16E-05 | -1.49E-01 |
| EP - freshwater | kg PO ₄ ³⁻ eq. | 4.79E-05 | 7.79E-10 | 2.64E-06 | 1.55E-07 | 7.19E-07 | 2.73E-09 | -1.13E-05 |
| EP - marine | kg N eq. | 2.91E-02 | 1.15E-06 | 3.97E-04 | 2.29E-04 | 8.17E-05 | 3.00E-06 | -2.13E-02 |
| EP - terrestrial | mol N eq. | 3.17E-01 | 1.27E-05 | 4.18E-03 | 2.53E-03 | 8.54E-04 | 3.30E-05 | -2.33E-01 |
| РОСР | kg NMVOC eq. | 8.68E-02 | 2.18E-06 | 1.07E-03 | 4.35E-04 | 2.06E-04 | 9.10E-06 | -6.45E-02 |
| ADP-MM (**) | kg Sb eq. | 1.55E-05 | 2.37E-11 | 1.09E-07 | 4.71E-09 | 6.46E-08 | 1.53E-10 | -5.75E-06 |
| ADPF (**) | MJ | 4.75E+02 | 4.54E-03 | 1.49E+01 | 9.03E-01 | 2.15E+00 | 2.16E-02 | -3.13E+02 |
| WDP (**) | m ³ | 6.54E+00 | 1.74E-06 | 1.55E-01 | 3.46E-04 | 3.82E-03 | 1.74E-04 | -3.80E+00 |

Note: GWP – Global Warming Potential; ODP – Ozone Depletion; AP – acidification potential for soil and water; EP – Eutrophication potential; POCP – formation potential of tropospheric ozone; ADP - MM – abiotic depletion potential for non fossil resources; ADPF – Abiotic depletion potential for fossil resources; WDP – Water deprivation potential.



Table 22 Core Environmental impacts indicators for 1 m^2 Anodised sheet for architectural cladding – 2 mm of aluminium sheet thickness and 20 μ m of anodic layer thickness

| Impact category | Unit | A1-A3 | A4 | C1 | C2 | C3 | C4 | D |
|---------------------|-----------------|----------|-----------|----------|-----------|----------|-----------|-----------|
| GWP - total | kg CO₂ eq. | 3.59E+01 | 3.33E-04 | 7.31E-01 | 6.63E-02 | 1.72E-01 | 1.58E-03 | -2.56E+01 |
| GWP – fossil | kg CO₂ eq. | 3.59E+01 | 3.32E-04 | 7.23E-01 | 6.62E-02 | 1.70E-01 | 1.62E-03 | -2.56E+01 |
| GWP – biogenic | kg CO₂ eq. | 6.09E-02 | -1.23E-06 | 7.59E-03 | -2.45E-04 | 1.06E-03 | -4.72E-05 | -5.34E-02 |
| GWP - luluc | kg CO₂ eq. | 9.47E-03 | 2.00E-06 | 1.80E-04 | 3.98E-04 | 4.14E-04 | 4.77E-06 | -4.34E-03 |
| ODP | kg CFC 11 eq. | 2.77E-10 | 5.85E-17 | 1.29E-11 | 1.16E-14 | 5.34E-15 | 6.31E-18 | -1.92E-10 |
| АР | mol H⁺ eq. | 1.79E-01 | 2.31E-06 | 1.58E-03 | 4.59E-04 | 2.92E-04 | 1.16E-05 | -1.49E-01 |
| EP - freshwater | kg PO₄³- eq. | 4.87E-05 | 7.79E-10 | 2.64E-06 | 1.55E-07 | 7.19E-07 | 2.73E-09 | -1.13E-05 |
| EP - marine | kg N eq. | 2.92E-02 | 1.15E-06 | 3.97E-04 | 2.29E-04 | 8.17E-05 | 3.00E-06 | -2.13E-02 |
| EP - terrestrial | mol N eq. | 3.18E-01 | 1.27E-05 | 4.18E-03 | 2.53E-03 | 8.54E-04 | 3.30E-05 | -2.33E-01 |
| РОСР | kg NMVOC eq. | 8.71E-02 | 2.18E-06 | 1.07E-03 | 4.35E-04 | 2.06E-04 | 9.10E-06 | -6.45E-02 |
| ADP-MM (**) | kg Sb eq. | 1.55E-05 | 2.37E-11 | 1.09E-07 | 4.71E-09 | 6.46E-08 | 1.53E-10 | -5.75E-06 |
| ADPF (**) | MJ | 4.81E+02 | 4.54E-03 | 1.49E+01 | 9.03E-01 | 2.15E+00 | 2.16E-02 | -3.13E+02 |
| WDP (**) | m ³ | 6.58E+00 | 1.74E-06 | 1.55E-01 | 3.46E-04 | 3.82E-03 | 1.74E-04 | -3.80E+00 |

Note: GWP – Global Warming Potential; ODP – Ozone Depletion; AP – acidification potential for soil and water; EP – Eutrophication potential; POCP – formation potential of tropospheric ozone; ADP - MM – abiotic depletion potential for non fossil resources; ADPF – Abiotic depletion potential for fossil resources; WDP – Water deprivation potential.





5.1.1 Additional Environmental impacts indicators

Table 23 Additional Environmental impacts indicators for 1 m^2 Anodised sheet for architectural cladding – 2 mm of aluminium sheet thickness and 10 μ m of anodic layer thickness

| Impact category | Unit | A1-A3 | A4 | C1 | C2 | С3 | C4 | D |
|---|--------------------------|----------|----------|----------|----------|----------|----------|-----------|
| Particular Matter emissions | Disease inciden ce | 2.37E-06 | 7.65E-12 | 1.35E-08 | 1.52E-09 | 2.15E-09 | 1.44E-10 | -2.08E-06 |
| lonising radiation - human health (*) | [kBq U235 eq.] | 5.39E+00 | 4.89E-07 | 3.88E-01 | 9.73E-05 | 2.00E-02 | 2.37E-05 | -3.58E+00 |
| Eco-toxicity (freshwate r) (**) | [CTUe] | 1.52E+02 | 3.37E-03 | 6.64E+00 | 6.71E-01 | 8.58E-01 | 1.23E-02 | -1.03E+02 |
| Human toxicity - cancer effects (**) | [CTUh] | 8.14E-09 | 6.74E-14 | 2.19E-10 | 1.34E-11 | 1.19E-10 | 1.81E-12 | -6.44E-09 |
| Human toxicity - non-cancer effects (**) | [CTUh] | 2.43E-07 | 3.63E-12 | 5.51E-09 | 7.22E-10 | 9.78E-10 | 2.00E-10 | -1.86E-07 |
| Land Use related impacts/ Soil quality (**) | dimensi onless | 4.51E+01 | 1.61E-03 | 5.84E+00 | 3.21E-01 | 1.06E+00 | 4.35E-03 | -9.09E+00 |

(*) **Disclaimer**: This impact category deals mainly with the eventual impact of low dose ionizing radiation on human health of the nuclear fuel cycle. It does not consider effects due to possible nuclear accidents, occupational exposure nor due to radioactive waste disposal in underground facilities. Potential ionizing radiation from the soil, from radon and from some construction materials is also not measured by this indicator.



Table 24 Additional Environmental impacts indicators for 1 m^2 Anodised sheet for architectural cladding - 2 mm of aluminium sheet thickness and 15 μ m of anodic layer thickness

| Impact category | Unit | A1-A3 | A4 | C1 | C2 | C3 | C4 | D |
|---|--------------------------|----------|----------|----------|----------|----------|----------|-----------|
| Particular Matter emissions | Disease inciden ce | 2.37E-06 | 7.65E-12 | 1.35E-08 | 1.52E-09 | 2.15E-09 | 1.44E-10 | -2.08E-06 |
| lonising radiation - human health (*) | [kBq U235 eq.] | 5.41E+00 | 4.89E-07 | 3.88E-01 | 9.73E-05 | 2.00E-02 | 2.37E-05 | -3.58E+00 |
| Eco-toxicity (freshwate r) (**) | [CTUe] | 1.53E+02 | 3.37E-03 | 6.64E+00 | 6.71E-01 | 8.58E-01 | 1.23E-02 | -1.03E+02 |
| Human toxicity - cancer effects (**) | [CTUh] | 8.16E-09 | 6.74E-14 | 2.19E-10 | 1.34E-11 | 1.19E-10 | 1.81E-12 | -6.44E-09 |
| Human toxicity - non-cancer effects (**) | [CTUh] | 2.44E-07 | 3.63E-12 | 5.51E-09 | 7.22E-10 | 9.78E-10 | 2.00E-10 | -1.86E-07 |
| Land Use related impacts/ Soil quality (**) | dimensi onless | 4.55E+01 | 1.61E-03 | 5.84E+00 | 3.21E-01 | 1.06E+00 | 4.35E-03 | -9.09E+00 |

(*) **Disclaimer**: This impact category deals mainly with the eventual impact of low dose ionizing radiation on human health of the nuclear fuel cycle. It does not consider effects due to possible nuclear accidents, occupational exposure nor due to radioactive waste disposal in underground facilities. Potential ionizing radiation from the soil, from radon and from some construction materials is also not measured by this indicator.



Table 25 Additional Environmental impacts indicators for 1 m^2 Anodised sheet for architectural cladding – 2 mm of aluminium sheet thickness and 20 μ m of anodic layer thickness

| Impact category | Unit | A1-A3 | A4 | C1 | C2 | C3 | C4 | D |
|---|--------------------------|----------|----------|----------|----------|----------|----------|-----------|
| Particular Matter emissions | Disease inciden ce | 2.37E-06 | 7.65E-12 | 1.35E-08 | 1.52E-09 | 2.15E-09 | 1.44E-10 | -2.08E-06 |
| lonising radiation - human health (*) | [kBq U235 eq.] | 5.52E+00 | 4.89E-07 | 3.88E-01 | 9.73E-05 | 2.00E-02 | 2.37E-05 | -3.58E+00 |
| Eco-toxicity (freshwate r) (**) | [CTUe] | 1.55E+02 | 3.37E-03 | 6.64E+00 | 6.71E-01 | 8.58E-01 | 1.23E-02 | -1.03E+02 |
| Human toxicity - cancer effects (**) | [CTUh] | 8.24E-09 | 6.74E-14 | 2.19E-10 | 1.34E-11 | 1.19E-10 | 1.81E-12 | -6.44E-09 |
| Human toxicity - non-cancer effects (**) | [CTUh] | 2.46E-07 | 3.63E-12 | 5.51E-09 | 7.22E-10 | 9.78E-10 | 2.00E-10 | -1.86E-07 |
| Land Use related impacts/ Soil quality (**) | dimensi onless | 4.71E+01 | 1.61E-03 | 5.84E+00 | 3.21E-01 | 1.06E+00 | 4.35E-03 | -9.09E+00 |

(*) **Disclaimer**: This impact category deals mainly with the eventual impact of low dose ionizing radiation on human health of the nuclear fuel cycle. It does not consider effects due to possible nuclear accidents, occupational exposure nor due to radioactive waste disposal in underground facilities. Potential ionizing radiation from the soil, from radon and from some construction materials is also not measured by this indicator.



5.2 Resource use

Table 26 Resource use for 1 m^2 Anodised sheet for architectural cladding - 2 mm of aluminium sheet thickness and 10 μ m of anodic layer thickness

| Parameter | Unit | A1-A3 | A4 | C1 | C2 | С3 | C4 | D |
|-----------|------|----------|----------|----------|----------|----------|----------|-----------|
| PERE | MJ | 1.87E+02 | 2.93E-04 | 8.78E+00 | 5.84E-02 | 1.16E+00 | 2.90E-03 | -1.42E+02 |
| PERM | MJ | 0.00E+00 |
| PERT | MJ | 1.87E+02 | 2.93E-04 | 8.78E+00 | 5.84E-02 | 1.16E+00 | 2.90E-03 | -1.42E+02 |
| PENRE | MJ | 4.73E+02 | 4.54E-03 | 1.49E+01 | 9.03E-01 | 2.15E+00 | 2.16E-02 | -3.14E+02 |
| PENRM | MJ | 0.00E+00 |
| PENRT | MJ | 4.73E+02 | 4.54E-03 | 1.49E+01 | 9.03E-01 | 2.15E+00 | 2.16E-02 | -3.14E+02 |
| SM | kg | 2.34E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 |
| RSF | MJ | 0.00E+00 |
| NRSF | MJ | 0.00E+00 |
| FW | m³ | 4.59E-01 | 2.67E-07 | 7.09E-03 | 5.32E-05 | 6.26E-04 | 5.32E-06 | -3.61E-01 |

Note: PERE – use of renewable primary energy resources used as raw materials; PERT – Total use of renewable primary energy resources; PENRE – use of non-renewable primary energy excluding non-renewable primary energy resources used as raw materials; PENRM – use of non-renewable primary energy resources used as raw materials; PENRT – Total use of non-renewable primary energy resources used as raw materials; PENRT – Total use of non-renewable primary energy resources used as raw materials; PENRT – Total use of non-renewable primary energy resources used as raw materials; PENRT – Total use of non-renewable primary energy resources used as raw materials; PENRT – Total use of non-renewable primary energy resources; SM – Use of secondary materials; RSF – Use of renewable secondary fuels; NRSF – use of non-renewable secondary fuels; FW – use of net fresh water.

Table 27 Resource use for 1 m^2 Anodised sheet for architectural cladding - 2 mm of aluminium sheet thickness and 15 μ m of anodic layer thickness

| Parameter | Unit | A1-A3 | A4 | C1 | C2 | C3 | C4 | D |
|-----------|------|----------|----------|----------|----------|----------|----------|-----------|
| PERE | MJ | 1.88E+02 | 2.93E-04 | 8.78E+00 | 5.84E-02 | 1.16E+00 | 2.90E-03 | -1.42E+02 |
| PERM | MJ | 0.00E+00 |
| PERT | MJ | 1.88E+02 | 2.93E-04 | 8.78E+00 | 5.84E-02 | 1.16E+00 | 2.90E-03 | -1.42E+02 |
| PENRE | MJ | 4.75E+02 | 4.54E-03 | 1.49E+01 | 9.03E-01 | 2.15E+00 | 2.16E-02 | -3.14E+02 |
| PENRM | MJ | 0.00E+00 |
| PENRT | MJ | 4.75E+02 | 4.54E-03 | 1.49E+01 | 9.03E-01 | 2.15E+00 | 2.16E-02 | -3.14E+02 |
| SM | kg | 2.34E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 |
| RSF | MJ | 0.00E+00 |
| NRSF | MJ | 0.00E+00 |
| FW | m³ | 4.59E-01 | 2.67E-07 | 7.09E-03 | 5.32E-05 | 6.26E-04 | 5.32E-06 | -3.61E-01 |

Note: PERE – use of renewable primary energy resources used as raw materials; PERT – Total use of renewable primary energy resources; PENRE – use of non-renewable primary energy excluding non-renewable primary energy resources used as raw materials; PENRM – use of non-renewable primary energy resources used as raw materials; PENRT – Total use of non-renewable primary energy resources used as raw materials; PENRT – Total use of non-renewable primary energy resources used as raw materials; PENRT – Total use of non-renewable primary energy resources used as raw materials; PENRT – Total use of non-renewable primary energy resources used as raw materials; PENRT – Total use of non-renewable primary energy resources; SM – Use of secondary materials; RSF – Use of renewable secondary fuels; NRSF – use of non-renewable secondary fuels; FW – use of net fresh water.



Table 28 Resource use for 1 m^2 Anodised sheet for architectural cladding - 2 mm of aluminium sheet thickness and 20 μ m of anodic layer thickness

| Parameter | Unit | A1-A3 | A4 | C1 | C2 | С3 | C4 | D |
|-----------|------|----------|----------|----------|----------|----------|----------|-----------|
| PERE | MJ | 1.90E+02 | 2.93E-04 | 8.78E+00 | 5.84E-02 | 1.16E+00 | 2.90E-03 | -1.42E+02 |
| PERM | MJ | 0.00E+00 |
| PERT | MJ | 1.90E+02 | 2.93E-04 | 8.78E+00 | 5.84E-02 | 1.16E+00 | 2.90E-03 | -1.42E+02 |
| PENRE | MJ | 4.81E+02 | 4.54E-03 | 1.49E+01 | 9.03E-01 | 2.15E+00 | 2.16E-02 | -3.14E+02 |
| PENRM | MJ | 0.00E+00 |
| PENRT | MJ | 4.81E+02 | 4.54E-03 | 1.49E+01 | 9.03E-01 | 2.15E+00 | 2.16E-02 | -3.14E+02 |
| SM | kg | 2.34E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 |
| RSF | MJ | 0.00E+00 |
| NRSF | MJ | 0.00E+00 |
| FW | m³ | 4.61E-01 | 2.67E-07 | 7.09E-03 | 5.32E-05 | 6.26E-04 | 5.32E-06 | -3.61E-01 |

Note: PERE – use of renewable primary energy resources used as raw materials; PERT – Total use of renewable primary energy resources; PENRE – use of non-renewable primary energy excluding non-renewable primary energy resources used as raw materials; PENRM – use of non-renewable primary energy resources used as raw materials; PENRT – Total use of non-renewable primary energy resources used as raw materials; PENRT – Total use of non-renewable primary energy resources used as raw materials; PENRT – Total use of non-renewable primary energy resources used as raw materials; PENRT – Total use of non-renewable primary energy resources; SM – Use of secondary materials; RSF – Use of renewable secondary fuels; NRSF – use of non-renewable secondary fuels; FW – use of net fresh water.



5.3 Output flows, waste categories

Table 29 Output flows, waste categories for 1 m^2 Anodised sheet for architectural cladding - 2 mm of aluminium sheet thickness and 10 μ m of anodic layer thickness

| Parameter | Unit | A1-A3 | A4 | C1 | C2 | С3 | C4 | D |
|-----------|------|----------|----------|-----------|----------|----------|----------|-----------|
| HWD | kg | 3.05E-07 | 1.22E-14 | -1.15E-09 | 2.42E-12 | 1.67E-09 | 2.29E-12 | -2.21E-07 |
| NHWD | kg | 8.90E+00 | 6.62E-07 | 1.08E-02 | 1.32E-04 | 2.23E-03 | 1.08E-01 | -7.67E+00 |
| RWD | kg | 2.98E-02 | 4.75E-09 | 2.33E-03 | 9.44E-07 | 2.03E-04 | 2.26E-07 | -1.87E-02 |
| CRU | kg | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 |
| MFR | kg | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 5.29E+00 | 0.00E+00 | 0.00E+00 |
| MER | kg | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 |
| EEE | MJ | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 |
| EET | MJ | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 |

Note: HWD – hazardous waste disposed; NHWD – Non-hazardous waste disposed; RWD – Radioactive waste disposed; CRU – Components for re-use; MFR – Materials for recycling; MER – Materials for energy recovery; EEE – Exported electrical energy; EET – Exported thermal energy

Table 30 Output flows, waste categories for $1 m^2$ Anodised sheet for architectural cladding - 2 mm of aluminium sheet thickness and 15 μ m of anodic layer thickness

| Parameter | Unit | A1-A3 | A4 | C1 | C2 | С3 | C4 | D |
|-----------|------|----------|----------|-----------|----------|----------|----------|-----------|
| HWD | kg | 3.05E-07 | 1.22E-14 | -1.15E-09 | 2.42E-12 | 1.67E-09 | 2.29E-12 | -2.21E-07 |
| NHWD | kg | 8.90E+00 | 6.62E-07 | 1.08E-02 | 1.32E-04 | 2.23E-03 | 1.08E-01 | -7.67E+00 |
| RWD | kg | 3.00E-02 | 4.75E-09 | 2.33E-03 | 9.44E-07 | 2.03E-04 | 2.26E-07 | -1.87E-02 |
| CRU | kg | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 |
| MFR | kg | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 5.29E+00 | 0.00E+00 | 0.00E+00 |
| MER | kg | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 |
| EEE | MJ | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 |
| EET | MJ | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 |

Note: HWD – hazardous waste disposed; NHWD – Non-hazardous waste disposed; RWD – Radioactive waste disposed; CRU – Components for re-use; MFR – Materials for recycling; MER – Materials for energy recovery; EEE – Exported electrical energy; EET – Exported thermal energy

Table 31 Output flows, waste categories for 1 m^2 Anodised sheet for architectural cladding - 2 mm of aluminium sheet thickness and 20 μ m of anodic layer thickness

| Parameter | Unit | A1-A3 | A4 | C1 | C2 | С3 | C4 | D |
|-----------|------|----------|----------|-----------|----------|----------|----------|-----------|
| HWD | kg | 3.05E-07 | 1.22E-14 | -1.15E-09 | 2.42E-12 | 1.67E-09 | 2.29E-12 | -2.21E-07 |
| NHWD | kg | 8.91E+00 | 6.62E-07 | 1.08E-02 | 1.32E-04 | 2.23E-03 | 1.08E-01 | -7.67E+00 |
| RWD | kg | 3.06E-02 | 4.75E-09 | 2.33E-03 | 9.44E-07 | 2.03E-04 | 2.26E-07 | -1.87E-02 |
| CRU | kg | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 |
| MFR | kg | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 5.29E+00 | 0.00E+00 | 0.00E+00 |
| MER | kg | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 |
| EEE | MJ | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 |
| EET | MJ | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 |

Note: HWD – hazardous waste disposed; NHWD – Non-hazardous waste disposed; RWD – Radioactive waste disposed; CRU – Components for re-use; MFR – Materials for recycling; MER – Materials for energy recovery; EEE – Exported electrical energy; EET – Exported thermal energy



6 LCA RESULTS – ANODISED SHEET FOR ARCHITECTURAL CLADDING – 3 mm sheet thickness; 10, 15, 20 μm anodic layer

6.1 Core Environmental impacts indicators

Table 32 Core Environmental impacts indicators for 1 m^2 Anodised sheet for architectural cladding – 3 mm of aluminium sheet thickness and 10 μ m of anodic layer thickness

| Impact category | Unit | A1-A3 | A4 | C1 | C2 | C3 | C4 | D |
|---------------------|--------------------------------------|----------|-----------|----------|-----------|----------|-----------|-----------|
| GWP - total | kg CO₂ eq. | 5.15E+01 | 5.00E-04 | 1.11E+00 | 9.95E-02 | 2.57E-01 | 2.37E-03 | -3.84E+01 |
| GWP – fossil | kg CO₂ eq. | 5.15E+01 | 4.99E-04 | 1.10E+00 | 9.92E-02 | 2.55E-01 | 2.44E-03 | -3.83E+01 |
| GWP – biogenic | kg CO₂ eq. | 6.38E-02 | -1.85E-06 | 1.14E-02 | -3.68E-04 | 1.58E-03 | -7.08E-05 | -8.02E-02 |
| GWP - luluc | kg CO₂ eq. | 1.40E-02 | 3.00E-06 | 3.48E-04 | 5.97E-04 | 6.21E-04 | 7.16E-06 | -6.51E-03 |
| ODP | kg CFC 11 eq. | 3.93E-10 | 8.78E-17 | 1.93E-11 | 1.75E-14 | 8.02E-15 | 9.47E-18 | -2.88E-10 |
| АР | mol H⁺ eq. | 2.65E-01 | 3.46E-06 | 2.43E-03 | 6.88E-04 | 4.37E-04 | 1.74E-05 | -2.23E-01 |
| EP - freshwater | kg PO ₄ ³⁻ eq. | 5.79E-05 | 1.17E-09 | 3.99E-06 | 2.33E-07 | 1.08E-06 | 4.09E-09 | -1.70E-05 |
| EP - marine | kg N eq. | 4.29E-02 | 1.73E-06 | 6.27E-04 | 3.44E-04 | 1.23E-04 | 4.51E-06 | -3.20E-02 |
| EP - terrestrial | mol N eq. | 4.67E-01 | 1.91E-05 | 6.61E-03 | 3.80E-03 | 1.28E-03 | 4.95E-05 | -3.49E-01 |
| РОСР | kg NMVOC eq. | 1.28E-01 | 3.28E-06 | 1.69E-03 | 6.52E-04 | 3.09E-04 | 1.37E-05 | -9.67E-02 |
| ADP-MM (**) | kg Sb eq. | 1.90E-05 | 3.55E-11 | 1.65E-07 | 7.07E-09 | 9.68E-08 | 2.30E-10 | -8.62E-06 |
| ADPF (**) | MJ | 6.78E+02 | 6.80E-03 | 2.25E+01 | 1.35E+00 | 3.23E+00 | 3.23E-02 | -4.70E+02 |
| WDP (**) | m ³ | 8.78E+00 | 2.61E-06 | 2.33E-01 | 5.19E-04 | 5.73E-03 | 2.62E-04 | -5.69E+00 |

Note: GWP – Global Warming Potential; ODP – Ozone Depletion; AP – acidification potential for soil and water; EP – Eutrophication potential; POCP – formation potential of tropospheric ozone; ADP - MM – abiotic depletion potential for non fossil resources; ADPF – Abiotic depletion potential for fossil resources; WDP – Water deprivation potential.



Table 33 Core Environmental impacts indicators for 1 m^2 Anodised sheet for architectural cladding - 3 mm of aluminium sheet thickness and 15 μ m of anodic layer thickness

| Impact category | Unit | A1-A3 | A4 | C1 | C2 | C3 | C4 | D |
|---------------------|-----------------|----------|-----------|----------|-----------|----------|-----------|-----------|
| GWP - total | kg CO₂ eq. | 5.17E+01 | 5.00E-04 | 1.11E+00 | 9.95E-02 | 2.57E-01 | 2.37E-03 | -3.84E+01 |
| GWP – fossil | kg CO₂ eq. | 5.16E+01 | 4.99E-04 | 1.10E+00 | 9.92E-02 | 2.55E-01 | 2.44E-03 | -3.83E+01 |
| GWP – biogenic | kg CO₂ eq. | 6.44E-02 | -1.85E-06 | 1.14E-02 | -3.68E-04 | 1.58E-03 | -7.08E-05 | -8.02E-02 |
| GWP - luluc | kg CO₂ eq. | 1.40E-02 | 3.00E-06 | 3.48E-04 | 5.97E-04 | 6.21E-04 | 7.16E-06 | -6.51E-03 |
| ODP | kg CFC 11 eq. | 3.93E-10 | 8.78E-17 | 1.93E-11 | 1.75E-14 | 8.02E-15 | 9.47E-18 | -2.88E-10 |
| АР | mol H⁺ eq. | 2.65E-01 | 3.46E-06 | 2.43E-03 | 6.88E-04 | 4.37E-04 | 1.74E-05 | -2.23E-01 |
| EP - freshwater | kg PO₄³- eq. | 5.81E-05 | 1.17E-09 | 3.99E-06 | 2.33E-07 | 1.08E-06 | 4.09E-09 | -1.70E-05 |
| EP - marine | kg N eq. | 4.29E-02 | 1.73E-06 | 6.27E-04 | 3.44E-04 | 1.23E-04 | 4.51E-06 | -3.20E-02 |
| EP - terrestrial | mol N eq. | 4.68E-01 | 1.91E-05 | 6.61E-03 | 3.80E-03 | 1.28E-03 | 4.95E-05 | -3.49E-01 |
| РОСР | kg NMVOC eq. | 1.28E-01 | 3.28E-06 | 1.69E-03 | 6.52E-04 | 3.09E-04 | 1.37E-05 | -9.67E-02 |
| ADP-MM (**) | kg Sb eq. | 1.90E-05 | 3.55E-11 | 1.65E-07 | 7.07E-09 | 9.68E-08 | 2.30E-10 | -8.62E-06 |
| ADPF (**) | MJ | 6.80E+02 | 6.80E-03 | 2.25E+01 | 1.35E+00 | 3.23E+00 | 3.23E-02 | -4.70E+02 |
| WDP (**) | m ³ | 8.79E+00 | 2.61E-06 | 2.33E-01 | 5.19E-04 | 5.73E-03 | 2.62E-04 | -5.69E+00 |

Note: GWP – Global Warming Potential; ODP – Ozone Depletion; AP – acidification potential for soil and water; EP – Eutrophication potential; POCP – formation potential of tropospheric ozone; ADP - MM – abiotic depletion potential for non fossil resources; ADPF – Abiotic depletion potential for fossil resources; WDP – Water deprivation potential.



Table 34 Core Environmental impacts indicators for 1 m^2 Anodised sheet for architectural cladding – 3 mm of aluminium sheet thickness and 20 μ m of anodic layer thickness

| Impact category | Unit | A1-A3 | A4 | C1 | C2 | C3 | C4 | D |
|---------------------|------------------------|----------|-----------|----------|-----------|----------|-----------|-----------|
| GWP - total | kg CO ₂ eq. | 5.20E+01 | 5.00E-04 | 1.11E+00 | 9.95E-02 | 2.57E-01 | 2.37E-03 | -3.84E+01 |
| GWP – fossil | kg CO₂ eq. | 5.19E+01 | 4.99E-04 | 1.10E+00 | 9.92E-02 | 2.55E-01 | 2.44E-03 | -3.83E+01 |
| GWP – biogenic | kg CO₂ eq. | 6.67E-02 | -1.85E-06 | 1.14E-02 | -3.68E-04 | 1.58E-03 | -7.08E-05 | -8.02E-02 |
| GWP - luluc | kg CO₂ eq. | 1.40E-02 | 3.00E-06 | 3.48E-04 | 5.97E-04 | 6.21E-04 | 7.16E-06 | -6.51E-03 |
| ODP | kg CFC 11 eq. | 3.97E-10 | 8.78E-17 | 1.93E-11 | 1.75E-14 | 8.02E-15 | 9.47E-18 | -2.88E-10 |
| АР | mol H⁺ eq. | 2.65E-01 | 3.46E-06 | 2.43E-03 | 6.88E-04 | 4.37E-04 | 1.74E-05 | -2.23E-01 |
| EP - freshwater | kg PO₄³- eq. | 5.88E-05 | 1.17E-09 | 3.99E-06 | 2.33E-07 | 1.08E-06 | 4.09E-09 | -1.70E-05 |
| EP - marine | kg N eq. | 4.31E-02 | 1.73E-06 | 6.27E-04 | 3.44E-04 | 1.23E-04 | 4.51E-06 | -3.20E-02 |
| EP - terrestrial | mol N eq. | 4.69E-01 | 1.91E-05 | 6.61E-03 | 3.80E-03 | 1.28E-03 | 4.95E-05 | -3.49E-01 |
| РОСР | kg NMVOC eq. | 1.29E-01 | 3.28E-06 | 1.69E-03 | 6.52E-04 | 3.09E-04 | 1.37E-05 | -9.67E-02 |
| ADP-MM (**) | kg Sb eq. | 1.90E-05 | 3.55E-11 | 1.65E-07 | 7.07E-09 | 9.68E-08 | 2.30E-10 | -8.62E-06 |
| ADPF (**) | MJ | 6.86E+02 | 6.80E-03 | 2.25E+01 | 1.35E+00 | 3.23E+00 | 3.23E-02 | -4.70E+02 |
| WDP (**) | m ³ | 8.84E+00 | 2.61E-06 | 2.33E-01 | 5.19E-04 | 5.73E-03 | 2.62E-04 | -5.69E+00 |

Note: GWP – Global Warming Potential; ODP – Ozone Depletion; AP – acidification potential for soil and water; EP – Eutrophication potential; POCP – formation potential of tropospheric ozone; ADP - MM – abiotic depletion potential for non fossil resources; ADPF – Abiotic depletion potential for fossil resources; WDP – Water deprivation potential.





6.1.1 Additional Environmental impacts indicators

Table 35 Additional Environmental impacts indicators for 1 m^2 Anodised sheet for architectural cladding – 3 mm of aluminium sheet thickness and 10 μ m of anodic layer thickness

| Impact category | Unit | A1-A3 | A4 | C1 | C2 | С3 | C4 | D |
|---|--------------------------|----------|----------|----------|----------|----------|----------|-----------|
| Particular Matter emissions | Disease inciden ce | 3.53E-06 | 1.15E-11 | 2.10E-08 | 2.28E-09 | 3.23E-09 | 2.16E-10 | -3.12E-06 |
| lonising radiation - human health (*) | [kBq U235 eq.] | 7.59E+00 | 7.33E-07 | 5.82E-01 | 1.46E-04 | 2.99E-02 | 3.56E-05 | -5.37E+00 |
| Eco-toxicity (freshwate r) (**) | [CTUe] | 2.19E+02 | 5.06E-03 | 1.01E+01 | 1.01E+00 | 1.29E+00 | 1.84E-02 | -1.55E+02 |
| Human toxicity - cancer effects (**) | [CTUh] | 1.18E-08 | 1.01E-13 | 3.32E-10 | 2.01E-11 | 1.78E-10 | 2.72E-12 | -9.67E-09 |
| Human toxicity - non-cancer effects (**) | [CTUh] | 3.52E-07 | 5.44E-12 | 8.42E-09 | 1.08E-09 | 1.47E-09 | 3.00E-10 | -2.78E-07 |
| Land Use related impacts/ Soil quality (**) | dimensi onless | 6.04E+01 | 2.42E-03 | 8.82E+00 | 4.81E-01 | 1.60E+00 | 6.53E-03 | -1.36E+01 |

(*) **Disclaimer**: This impact category deals mainly with the eventual impact of low dose ionizing radiation on human health of the nuclear fuel cycle. It does not consider effects due to possible nuclear accidents, occupational exposure nor due to radioactive waste disposal in underground facilities. Potential ionizing radiation from the soil, from radon and from some construction materials is also not measured by this indicator.



Table 36 Additional Environmental impacts indicators for 1 m^2 Anodised sheet for architectural cladding - 3 mm of aluminium sheet thickness and 15 μ m of anodic layer thickness

| Impact category | Unit | A1-A3 | A4 | C1 | C2 | C3 | C4 | D |
|---|--------------------------|----------|----------|----------|----------|----------|----------|-----------|
| Particular Matter emissions | Disease inciden ce | 3.53E-06 | 1.15E-11 | 2.10E-08 | 2.28E-09 | 3.23E-09 | 2.16E-10 | -3.12E-06 |
| lonising radiation - human health (*) | [kBq U235 eq.] | 7.62E+00 | 7.33E-07 | 5.82E-01 | 1.46E-04 | 2.99E-02 | 3.56E-05 | -5.37E+00 |
| Eco-toxicity (freshwate r) (**) | [CTUe] | 2.20E+02 | 5.06E-03 | 1.01E+01 | 1.01E+00 | 1.29E+00 | 1.84E-02 | -1.55E+02 |
| Human toxicity - cancer effects (**) | [CTUh] | 1.18E-08 | 1.01E-13 | 3.32E-10 | 2.01E-11 | 1.78E-10 | 2.72E-12 | -9.67E-09 |
| Human toxicity - non-cancer effects (**) | [CTUh] | 3.53E-07 | 5.44E-12 | 8.42E-09 | 1.08E-09 | 1.47E-09 | 3.00E-10 | -2.78E-07 |
| Land Use related impacts/ Soil quality (**) | dimensi onless | 6.07E+01 | 2.42E-03 | 8.82E+00 | 4.81E-01 | 1.60E+00 | 6.53E-03 | -1.36E+01 |

(*) **Disclaimer**: This impact category deals mainly with the eventual impact of low dose ionizing radiation on human health of the nuclear fuel cycle. It does not consider effects due to possible nuclear accidents, occupational exposure nor due to radioactive waste disposal in underground facilities. Potential ionizing radiation from the soil, from radon and from some construction materials is also not measured by this indicator.



Table 37 Additional Environmental impacts indicators for 1 m^2 Anodised sheet for architectural cladding – 3 mm of aluminium sheet thickness and 20 μ m of anodic layer thickness

| Impact category | Unit | A1-A3 | A4 | C1 | C2 | C3 | C4 | D |
|---|--------------------------|----------|----------|----------|----------|----------|----------|-----------|
| Particular Matter emissions | Disease inciden ce | 3.53E-06 | 1.15E-11 | 2.10E-08 | 2.28E-09 | 3.23E-09 | 2.16E-10 | -3.12E-06 |
| lonising radiation - human health (*) | [kBq U235 eq.] | 7.73E+00 | 7.33E-07 | 5.82E-01 | 1.46E-04 | 2.99E-02 | 3.56E-05 | -5.37E+00 |
| Eco-toxicity (freshwate r) (**) | [CTUe] | 2.22E+02 | 5.06E-03 | 1.01E+01 | 1.01E+00 | 1.29E+00 | 1.84E-02 | -1.55E+02 |
| Human toxicity - cancer effects (**) | [CTUh] | 1.19E-08 | 1.01E-13 | 3.32E-10 | 2.01E-11 | 1.78E-10 | 2.72E-12 | -9.67E-09 |
| Human toxicity - non-cancer effects (**) | [CTUh] | 3.55E-07 | 5.44E-12 | 8.42E-09 | 1.08E-09 | 1.47E-09 | 3.00E-10 | -2.78E-07 |
| Land Use related impacts/ Soil quality (**) | dimensi onless | 6.24E+01 | 2.42E-03 | 8.82E+00 | 4.81E-01 | 1.60E+00 | 6.53E-03 | -1.36E+01 |

(*) **Disclaimer**: This impact category deals mainly with the eventual impact of low dose ionizing radiation on human health of the nuclear fuel cycle. It does not consider effects due to possible nuclear accidents, occupational exposure nor due to radioactive waste disposal in underground facilities. Potential ionizing radiation from the soil, from radon and from some construction materials is also not measured by this indicator.



6.2 Resource use

Table 38 Resource use for 1 m^2 Anodised sheet for architectural cladding - 3 mm of aluminium sheet thickness and 10 μ m of anodic layer thickness

| Parameter | Unit | A1-A3 | A4 | C1 | C2 | С3 | C4 | D |
|-----------|------|----------|----------|----------|----------|----------|----------|-----------|
| PERE | MJ | 2.70E+02 | 4.40E-04 | 1.32E+01 | 8.76E-02 | 1.74E+00 | 4.35E-03 | -2.14E+02 |
| PERM | MJ | 0.00E+00 |
| PERT | MJ | 2.70E+02 | 4.40E-04 | 1.32E+01 | 8.76E-02 | 1.74E+00 | 4.35E-03 | -2.14E+02 |
| PENRE | MJ | 6.78E+02 | 6.81E-03 | 2.25E+01 | 1.35E+00 | 3.23E+00 | 3.24E-02 | -4.70E+02 |
| PENRM | MJ | 0.00E+00 |
| PENRT | MJ | 6.78E+02 | 6.81E-03 | 2.25E+01 | 1.35E+00 | 3.23E+00 | 3.24E-02 | -4.70E+02 |
| SM | kg | 3.51E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 |
| RSF | MJ | 0.00E+00 |
| NRSF | MJ | 0.00E+00 |
| FW | m³ | 6.61E-01 | 4.01E-07 | 1.06E-02 | 7.97E-05 | 9.39E-04 | 7.98E-06 | -5.41E-01 |

Note: PERE – use of renewable primary energy resources used as raw materials; PERT – Total use of renewable primary energy resources; PENRE – use of non-renewable primary energy excluding non-renewable primary energy resources used as raw materials; PENRM – use of non-renewable primary energy resources used as raw materials; PENRT – Total use of non-renewable primary energy resources used as raw materials; PENRT – Total use of non-renewable primary energy resources used as raw materials; PENRT – Total use of non-renewable primary energy resources used as raw materials; PENRT – Total use of non-renewable primary energy resources used as raw materials; PENRT – Total use of non-renewable primary energy resources; SM – Use of secondary materials; RSF – Use of renewable secondary fuels; NRSF – use of non-renewable secondary fuels; FW – use of net fresh water.

Table 39 Resource use for 1 m^2 Anodised sheet for architectural cladding - 3 mm of aluminium sheet thickness and 15 μ m of anodic layer thickness

| Parameter | Unit | A1-A3 | A4 | C1 | C2 | C3 | C4 | D |
|-----------|------|----------|----------|----------|----------|----------|----------|-----------|
| PERE | MJ | 2.70E+02 | 4.40E-04 | 1.32E+01 | 8.76E-02 | 1.74E+00 | 4.35E-03 | -2.14E+02 |
| PERM | MJ | 0.00E+00 |
| PERT | MJ | 2.70E+02 | 4.40E-04 | 1.32E+01 | 8.76E-02 | 1.74E+00 | 4.35E-03 | -2.14E+02 |
| PENRE | MJ | 6.81E+02 | 6.81E-03 | 2.25E+01 | 1.35E+00 | 3.23E+00 | 3.24E-02 | -4.70E+02 |
| PENRM | MJ | 0.00E+00 |
| PENRT | MJ | 6.81E+02 | 6.81E-03 | 2.25E+01 | 1.35E+00 | 3.23E+00 | 3.24E-02 | -4.70E+02 |
| SM | kg | 3.51E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 |
| RSF | MJ | 0.00E+00 |
| NRSF | MJ | 0.00E+00 |
| FW | m³ | 6.61E-01 | 4.01E-07 | 1.06E-02 | 7.97E-05 | 9.39E-04 | 7.98E-06 | -5.41E-01 |

Note: PERE – use of renewable primary energy resources used as raw materials; PERT – Total use of renewable primary energy resources; PENRE – use of non-renewable primary energy excluding non-renewable primary energy resources used as raw materials; PENRM – use of non-renewable primary energy resources used as raw materials; PENRT – Total use of non-renewable primary energy resources used as raw materials; PENRT – Total use of non-renewable primary energy resources used as raw materials; PENRT – Total use of non-renewable primary energy resources used as raw materials; PENRT – Total use of non-renewable primary energy resources used as raw materials; PENRT – Total use of non-renewable primary energy resources; SM – Use of secondary materials; RSF – Use of renewable secondary fuels; NRSF – use of non-renewable secondary fuels; FW – use of net fresh water.



Table 40 Resource use for 1 m^2 Anodised sheet for architectural cladding - 3 mm of aluminium sheet thickness and 20 μ m of anodic layer thickness

| Parameter | Unit | A1-A3 | A4 | C1 | C2 | С3 | C4 | D |
|-----------|------|----------|----------|----------|----------|----------|----------|-----------|
| PERE | MJ | 2.73E+02 | 4.40E-04 | 1.32E+01 | 8.76E-02 | 1.74E+00 | 4.35E-03 | -2.14E+02 |
| PERM | MJ | 0.00E+00 |
| PERT | MJ | 2.73E+02 | 4.40E-04 | 1.32E+01 | 8.76E-02 | 1.74E+00 | 4.35E-03 | -2.14E+02 |
| PENRE | MJ | 6.86E+02 | 6.81E-03 | 2.25E+01 | 1.35E+00 | 3.23E+00 | 3.24E-02 | -4.70E+02 |
| PENRM | MJ | 0.00E+00 |
| PENRT | MJ | 6.86E+02 | 6.81E-03 | 2.25E+01 | 1.35E+00 | 3.23E+00 | 3.24E-02 | -4.70E+02 |
| SM | kg | 3.51E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 |
| RSF | MJ | 0.00E+00 |
| NRSF | MJ | 0.00E+00 |
| FW | m³ | 6.63E-01 | 4.01E-07 | 1.06E-02 | 7.97E-05 | 9.39E-04 | 7.98E-06 | -5.41E-01 |

Note: PERE – use of renewable primary energy resources used as raw materials; PERT – Total use of renewable primary energy resources; PENRE – use of non-renewable primary energy excluding non-renewable primary energy resources used as raw materials; PENRM – use of non-renewable primary energy resources used as raw materials; PENRT – Total use of non-renewable primary energy resources used as raw materials; PENRT – Total use of non-renewable primary energy resources used as raw materials; PENRT – Total use of non-renewable primary energy resources used as raw materials; PENRT – Total use of non-renewable primary energy resources; SM – Use of secondary materials; RSF – Use of renewable secondary fuels; NRSF – use of non-renewable secondary fuels; FW – use of net fresh water.



6.3 Output flows, waste categories

Table 41 Output flows, waste categories for 1 m^2 Anodised sheet for architectural cladding - 3 mm of aluminium sheet thickness and 10 μ m of anodic layer thickness

| Parameter | Unit | A1-A3 | A4 | C1 | C2 | С3 | C4 | D |
|-----------|------|----------|----------|-----------|----------|----------|----------|-----------|
| HWD | kg | 4.56E-07 | 1.82E-14 | -1.72E-09 | 3.63E-12 | 2.51E-09 | 3.43E-12 | -3.32E-07 |
| NHWD | kg | 1.33E+01 | 9.93E-07 | 1.62E-02 | 1.98E-04 | 3.34E-03 | 1.61E-01 | -1.15E+01 |
| RWD | kg | 4.18E-02 | 7.12E-09 | 3.50E-03 | 1.42E-06 | 3.04E-04 | 3.39E-07 | -2.81E-02 |
| CRU | kg | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 |
| MFR | kg | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 7.94E+00 | 0.00E+00 | 0.00E+00 |
| MER | kg | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 |
| EEE | MJ | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 |
| EET | MJ | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 |

Note: HWD – hazardous waste disposed; NHWD – Non-hazardous waste disposed; RWD – Radioactive waste disposed; CRU – Components for re-use; MFR – Materials for recycling; MER – Materials for energy recovery; EEE – Exported electrical energy; EET – Exported thermal energy

Table 42 Output flows, waste categories for $1 m^2$ Anodised sheet for architectural cladding - 3 mm of aluminium sheet thickness and 15 μ m of anodic layer thickness

| Parameter | Unit | A1-A3 | A4 | C1 | C2 | С3 | C4 | D |
|-----------|------|----------|----------|-----------|----------|----------|----------|-----------|
| HWD | kg | 4.56E-07 | 1.82E-14 | -1.72E-09 | 3.63E-12 | 2.51E-09 | 3.43E-12 | -3.32E-07 |
| NHWD | kg | 1.33E+01 | 9.93E-07 | 1.62E-02 | 1.98E-04 | 3.34E-03 | 1.61E-01 | -1.15E+01 |
| RWD | kg | 4.20E-02 | 7.12E-09 | 3.50E-03 | 1.42E-06 | 3.04E-04 | 3.39E-07 | -2.81E-02 |
| CRU | kg | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 |
| MFR | kg | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 7.94E+00 | 0.00E+00 | 0.00E+00 |
| MER | kg | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 |
| EEE | MJ | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 |
| EET | MJ | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 |

Note: HWD – hazardous waste disposed; NHWD – Non-hazardous waste disposed; RWD – Radioactive waste disposed; CRU – Components for re-use; MFR – Materials for recycling; MER – Materials for energy recovery; EEE – Exported electrical energy; EET – Exported thermal energy

Table 43 Output flows, waste categories for 1 m^2 Anodised sheet for architectural cladding - 3 mm of aluminium sheet thickness and 20 μ m of anodic layer thickness

| Parameter | Unit | A1-A3 | A4 | C1 | C2 | С3 | C4 | D |
|-----------|------|----------|----------|-----------|----------|----------|----------|-----------|
| HWD | kg | 4.56E-07 | 1.82E-14 | -1.72E-09 | 3.63E-12 | 2.51E-09 | 3.43E-12 | -3.32E-07 |
| NHWD | kg | 1.33E+01 | 9.93E-07 | 1.62E-02 | 1.98E-04 | 3.34E-03 | 1.61E-01 | -1.15E+01 |
| RWD | kg | 4.26E-02 | 7.12E-09 | 3.50E-03 | 1.42E-06 | 3.04E-04 | 3.39E-07 | -2.81E-02 |
| CRU | kg | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 |
| MFR | kg | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 7.94E+00 | 0.00E+00 | 0.00E+00 |
| MER | kg | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 |
| EEE | MJ | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 |
| EET | MJ | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 |

Note: HWD – hazardous waste disposed; NHWD – Non-hazardous waste disposed; RWD – Radioactive waste disposed; CRU – Components for re-use; MFR – Materials for recycling; MER – Materials for energy recovery; EEE – Exported electrical energy; EET – Exported thermal energy



7 LCA – INTERPRETATION

The analysis of the LCIA results for all the products declared shows that most of the environmental impacts come from the aluminium coil and sheet manufacturing. Within the manufacturing processes, the primary aluminium production is dominant, especially the alumina production and the electrolysis. The rolling process, which converts ingot into coil, and the subsequent foreground anodising process contribute much less to the LCA results. The LCA modelling and the impact of the primary aluminium production are detailed in European Aluminium's environmental profile report.

The evolution of GWP of Module A1-A3 for the 3 sheet thicknesses is shown in the following diagram. Keeping the anodic layer thickness constant (we took 10 μ m as an example) and increasing the aluminium sheet thickness (doubling or tripling), the GWP increases by 45% and 62% respectively. The GWP values change from 1.95E+01 kg for the 1 mm-thick sheet to 3.55E+01 kg for the 2 mm-thick sheet to 5.15E+01 kg of CO₂-equiv for the 3 mm-thick sheet. The other indicators follow the same trends, e.g. ODP increases from 1.52E-10 to 2.72E-10 to 3.93E-10 [kg CFC11-eq.] and acidification potential from 9.22E-02 to 1.78E-01 to 2.65E-01 [kg SO₂-eq.].

Comparing the GWP value of European primary aluminium consumption (i.e. European production + net fraction of imports into Europe, as used in the present EPD) with that of European primary aluminium production scenario (i.e. using 100% of primary aluminium produced in Europe), the kg of CO_2 -eq. decreases by 16%, 18% and 19% for an Aluminium sheet thickness of 1mm, 2mm and 3m respectively.




Figure 2 Sensitivity analysis: EU consumption GWP against EU production GWP





• Anodising process (module A1-A3)

The anodising process only slightly influences the EPD results of anodised sheets, e.g. an increase of the anodic layer from 10 to 20 μ m generates an increase of the various indicators between 0 and 5% as illustrated in the next diagram for A1-A3 module considering 1 mm aluminium sheet thickness.




Figure 3 Comparison of GWP value between different anodic layers for the same thickness of aluminium sheet



8 OTHER INFORMATION

Novelis is a global player in the production of innovative aluminium products and solutions and one of the world's largest recyclers of aluminium. Our ambition is to be one of the leading providers of low-carbon, sustainable aluminium solutions and to achieve a fully circular economy by partnering with our suppliers, as well as our customers in the aerospace, automotive, beverage can and specialties industries throughout North America, Europe, Asia and South America.

As one of the world's largest recyclers of aluminium, we have a unique role to play in the aluminium value chain. We know that keeping aluminium "in the loop" is the best way for our industry to decarbonize. Therefore, we continue to innovate high recycled content alloys, invest in capacity and capability, and collaborate to scale circularity throughout our industry.

At Novelis, we view Corporate Social Responsibility as part of our ongoing commitment to achieve industry-leading economic and environmental goals, while simultaneously improving the quality of life for our employees and their families, the communities where we operate and society as a whole.

Through its Management Systems, certified according to ISO 9001:2015 and ISO 14001:2015, Novelis actively implements best practices regarding environmental protection through significant investments and measures, by optimizing the production cycle, implementing new procedures that reduce the energy footprint of our plants, and the vigilant prevention of any possibility of environmental pollution.

Additional information about Novelis's corporate responsibility and sustainability policy and the products can be found on the Novelis website <u>www.novelis.com</u>.





9 REFERENCES

European Aluminium General Programme Instructions version 3, 23rd of September 2020

European Aluminium (2018) ENVIRONMENTAL PROFILE REPORT Life-Cycle inventory data for aluminium production and transformation processes in Europe February 2018

EN 15804:2012+A2:2019, Sustainability of construction works - Environmental Product Declarations – Core rules for the product category of construction products.

ISO 14025:2006, Environmental labels and declarations -- Type III environmental declarations -- Principles and procedures.

EN 485-2:2016, Aluminium and aluminium alloys - Sheet, strip and plate - Part 2: Mechanical properties

EN 507:2019, Roofing and cladding products from metal sheet -- Specification for fully supported products of aluminum sheet.

EN 508-2:2019 Roofing and cladding products from metal sheet - Specification for self-supporting products of steel, aluminum, or stainless-steel sheet - Part 2: Aluminum.

EN 573-3:2019, Aluminum and aluminum alloys - Chemical composition and form of wrought products - Part 3: Chemical composition and form of products

EN 1396:2015, Aluminium and aluminium alloys - Coil coaproducts.t and strip for general applications - Specifications

EN 13501-1:2018, Fire classification of construction products and building elements -- Classification using data from reaction to fire tests.

EN 14782:2006, Self-supporting metal sheet for roofing, external cladding and internal lining - Product specification and requirements.

EN 14783:2013, Fully supported metal sheet and strip for roofing, external cladding and internal lining - Product specification and requirements.

EN 13964:2004/+A1:2006, Suspended ceilings - Requirements and test methods.

Please refer to the latest version of those standards.